3M

Release A, Effective September 2006

Scotchcal [™] Gloss Overlaminate 8518

Description

3M ™ Scotchcal ™ Gloss Overlaminate is a 2-mil film that can enhance gloss and provide additional ultraviolet and durable physical protection for selected digitally-imaged graphic constructions. It is designed for cold roll lamination only. Refer to the base film's Product Bulletin to determine compatibility and durability.

Characteristics

Characteristic	Description	
Color	Clear	
Gloss	Gloss	
Adhesive	Pressure sensitive, clear	
Liner	Polyester	
Thickness	2 mil (0.05 mm) without adhesive 3–4 mil (0.08 to 0.10 mm) with adhesive	
Tensile strength (minimum)	5 pounds/inch at 73°F (0.9 kg/cm at 23°C)	
Dimensional stability	0.015 inch (0.4 mm)	
In use temperature range	-65° to +225° F (-54° to +107° C)	
Chemical resistance	Resists mild alkalis, mild acids and salt	
	Excellent resistance to water	
	Resists petroleum vapors	

Shelf Life, Storage, and Shipping

Activity	Recommendation
Shelf life	Total shelf life: 2 years Up to 2 years unprocessed, OR process within 1 year and apply within 1 year of processing
Storage conditions	 86°F (30°C) maximum (Bring to room temperature before using) Out of sunlight Clean dry area Original container
Shipping finished graphics	Refer to the base film's Product Bulletin

Health and Safety

⚠ Caution

When handling any chemical products, read the manufacturers' container labels and the Material Safety Data Sheets (MSDS) for important health, safety and environmental information.

To obtain MSDS sheets for 3M products:

- By fax, call 1-800-364-0768 in the US and Canada or 1-650-556-8417 for all other locations.
- Electronically, visit us at http://www.3M.com/ MSDS.
- By mail, or in case of an emergency, call 1-800-364-3577 or 1-651-737-6501.

When using any equipment, always follow the manufacturers' instructions for safe operation.

Warranty and Limited Remedy

The following is made in lieu of all other express or implied warranties, including any implied warranty of merchantability or fitness for a particular purpose or implied warranty arising out of a course of dealing, custom or usage of trade: all 3M products are warranted to be free of defects in materials and manufacture at the time of shipment and to meet the specifications stated in this Product Bulletin. 3M will replace or refund the price of any unused 3M materials that do not meet this warranty. These remedies are exclusive. In no case shall 3M be liable for any direct, indirect, or consequential damages, including any labor or non–3M materials charges.

See the Graphics Market Center Warranty Brochure, which gives the terms, additional limitations of the warranty, if any, and limitations of liability.

3M Related Literature

Before starting any job, be sure you have the most current Product and Instruction Bulletins.

The information in 3M Product and Instruction Bulletins is subject to change. Current Bulletins, as well as a list of all Bulletins updated within the last three months, are available at www.scotchprint.com or through our Fax-on-Demand system. Any warranty, if offered, is based on information in the appropriate Bulletin(s) that was current at the time you purchased the 3M products. The following Product and/or Instruction Bulletins provide the information and processes you need to properly make the graphics described in this Bulletin.

Fax-on-Demand phone numbers: United States or Canada: 1-800-364-0768 International: 1-651-732-6506

Subject	Bulletin No.	FOD No.
Product Bulletins		
Films Please visit our Web site or our Fax-on-identify and order the base film bulletins ye	•	to
Instruction Bulletins		
Cold roll lamination	4.22	6522
Storage, handling, maintenance, removal	6.5	8505
Warranties		
Worldwide 3M Graphics Center Warranty Brochure		9503

3M

Graphics Market Center

3M Center, Building 220-12E-04 PO Box 33220 St. Paul, MN 55144-3220 USA General Info. 1-800-374-6772 Technical Info. 1-800-328-3908 Fax 1-651-736-4233

Fax-on-Demand 1-800-364-0768 US/Canada or 1-651-732-6506 International Fax-on-Demand document: 4600 www.3M.com/graphics

3M Canada

P.O. Box 5757 London, Ontario Canada N6A 4T1 1-800-265-1840 Fax 519-452-6245 3M México, S.A. de C.V.

Av. Santa Fe No. 55 Col. Santa Fe, Del. Alvaro Obregón México, D.F. 01210 52-55-52-70-04-00 Fax 52-55-52-70-22-77 3M Puerto Rico, Inc.

Puerto Rico Industrial Park P.O. Box 100 Carolina, PR 00986-0100 787-620-3000 Fax 787-750-3035

©3M 2006. All rights reserved.