

Preliminary Technical Data Sheet



ATP Mount

Product: GM- 624 FL TEXTBOND

Product Description:

TEXBBOND:

High bond strength scrim tape for use in a wide variety of materials, particularly suitable load-bearing bonding of banner materials (Textiles, Nonwovens, Canvas), Suitable for applications on even and structured surfaces. Suitable for indoor and outdoor applications. The TEXTBOND is supplied with a wider Polyolefinic filmic liner which prevents a bleeding of the transfer adhesive and leads to an easier applicability.

Product structure:

Support	PES/PVA scrim, diagonal
Interliner	Polyolefine foil, white, 80 µm
Adhesive	pure polyacrylic , permanent, transparent
Total Thickness	0,24 mm
Adhesive weight	240 g/m ²

Characteristics:

	Average Value	Test Method
Adhesion on steel: (after 20 min.)	25 N / 25mm	AFERA 5001
Adhesion on steel: (after 24 h)	35 N / 25mm	AFERA 5001

ATP adhesive systems AG
Sales International, R&D
Sihleggstr. 23, Postfach 127
CH - 8832 Wollerau
Telefon: +41(0)43/888-1515
Telefax: +41(0)43/888-1510
Email: info@atp-ag.ch

More Information can be found on:
www.atp-ag.com

02.07.2015

ATP adhesive systems GmbH
Vertrieb Deutschland
Eichenhofer Weg 71
D - 42279 Wuppertal
Telefon: +49(0)2339/909-750
Telefax: +49(0)2339/909-506
Email: info@atp-ag.com

Application temperature:	min. 10°C
End-Use Temperature range:	from -40°C to +100°C
Shelf life:	2 years (see application information)
Durability:	

The estimated durability is based on accelerated ageing tests and refers to a vertical exposure under middle European climates. The durability of the product depends on the substrate's preparation, the atmospheric conditions and the environmental influence. Exposure to extreme conditions (tropical climate, high humidity, high UV-light exposure or polluted areas) can decrease the durability in a dramatically way.

All our products are subjected to a strict quality control by our QM-System, which is in accordance with ISO/TS 16949, DIN EN ISO 9001 and DIN EN ISO 14001. The information is based on our present knowledge and our experience. Because of the large number of possible influences during the processing and application of our products, this information does not release the user from the obligation to conduct his own tests and trials. Users of our products are responsible for observing any patent rights that may exist and for following existing regulations. Our applications technology section is always pleased to give advice about suitability tests on original materials.